



**Check list for Décor:**

1. Minimum grade of the concrete should be M 25
  - a. 3" thickness for pedestrian traffic
  - b. 4" thickness for four vehicular traffic
2. Subgrade preparation should have a K-value of 8 or 0.08 N/mm<sup>3</sup> followed by 3" PCC above it
3. Curing should start within 2 hours of stamping process
4. Curing should be done by water sprinkling/ curing compound/ curing blanket (no jute bag curing allowed)
5. Control joint must be cut within 24 to 48 hours of concreting at 10 x 10 ft interval